

December 16, 2019

Mr. Joel Côté-Cright
DiZal Inc.
4000, Jean-Marchand
Québec, QC G2C 1Y6
CANADA

TEST REPORT # MI-19-11565

On November 22nd 2019, Micom Laboratories Inc. received 1 sample to perform Coefficient of Friction Testing.

SAMPLES DESCRIPTION:

- Sample 1 : 5.5" x 14"




Sample 1

This report shall not be reproduced except in full, without the written approval of the laboratory. The results herein relate only to the items tested.

REFERENCE TEST METHOD:

Sample was rated according to ASTM D2394 (Evaluating Degree of Rusting on Painted Steel Surfaces).

- Sliding unit weight : 25.53 Lbs
- Speed Rate : Static 0.05 in/min
Sliding 2 in/min



Typical setup used


This report shall not be reproduced except in full, without the written approval of the laboratory. The results herein relate only to the items tested.

RESULTS:

Tests performed between 2019-12-12 and 2019-12-13.

- Static Coefficients of Friction


Sample	ASTM D2394 Static Coefficients of Friction	
	Load (Lbf)	Coefficients
1	20.47	0.802



This report shall not be reproduced except in full, without the written approval of the laboratory. The results herein relate only to the items tested.

- Sliding Coefficients of Friction

Sample	ASTM D2394 Sliding Coefficients of Friction					Coefficients
	Load (Lbf)					
	Peak 1	Peak 2	Peak 3	Peak 4	Average	
1	17.38	16.94	16.83	16.63	16.95	0.663



Prepared by:

Approved by:

Adrien Mulot
Project Manager

Jacques St-Denis
Laboratories Supervisor

This report shall not be reproduced except in full, without the written approval of the laboratory. The results herein relate only to the items tested.